



# Sughera

The first closure made of cork **WITHOUT THE USE OF ANY GLUE**, thanks to a patented binding polymer with a special agglomerating agent. Sughera is strong, uniform in its dimension and constant on the oxygen permeability.

DIMENSION (mm)	DENSITY (kg/m <sup>3</sup> )	EXTRACTION FORCE (daN)	OTR (cc stopper/24h)	TCA (ng/L)
▼  ▲			▲  ▼	<b>OCH3Cl</b>  <b>Cl</b>  <b>Cl</b>
Ø22,5x38 mm Ø22,5x42,5 mm Ø23,5x42,5 mm	415-455	20-30	0.025-0.030 0.015-0.022 0.015-0.022	100% < SP*  * SP= 0,8 ng/L

## CUSTOMIZATION



to get more info, you can find all the characteristics on the technical sheet at the end of this catalogue

# Technical Comparison

		SUGHERA		
		Ø22,5x38	Ø22,5x42,5	Ø23,5x42,5
Dimensions (mm)	± 0,4 ± 0,5			
Chamfer(mm)	± 0,5	1-1		
Ovalization (mm)	< 0,5	-		
Density (kg/m³)	130-460	415-455		
Humidity(%)	5-8	-		
Rescue(%) Ø 5min	> 93	> 95		
Extraction force (daN)	20-40	20-30		
Capillarity(mm)	< 2,5	-		
OTR (cc stopper/24 H)		0.025-0.030 0.015-0.022		
Dustiness (mg)	< 2	-		
Sensorial(%)	< 2	-		
TCA (ng/L)	98% <SP*	100% <SP*		
(UFC/stopper)   Bacteria	< 30	FREE		
(UFC/stopper) Mildew and yeast	< 10	FREE		
(mg O2/stopper) Peroxide remains	< 0,2	FREE		



\* SP= 0,8 ng/L